

GLASS SOLUTIONS FOR **FACADES**

We play our part in designing some of the world's most iconic architectural projects, offering a wide range of innovative glazing solutions for façades. Partners such as visionary architects or contractors striving to deliver the ultimate building envelope have helped establish Saint-Gobain as a key glazing supplier to the global construction industry.

We respond to your needs with solar and heat control coatings, large dimensions, aesthetics, design, total transparency...

Our major field is specialized in providing glazing products ideal for hospitals, schools, office buildings, homes and other buildings where solar heat reduction and daylight are needed.

www.saint-gobain-glass.com



Solar Factor (g-value)

Percentage of solar energy transmitted through the glass. It measures the ability of a glazing to reduce the heating of the room. The lower the solar factor is, the better it helps to improve the comfort inside of the building.



Shading Coefficient (SC)

Ratio of the solar factor of a glazing unit to the solar factor of a clear float glass of nominal thickness of 3 mm to 4mm (0.87). The lower the shading coefficient number, the less heat gain and thus more shading is provided.



Selectivity (LSG)

Ratio between the glass' light transmission and solar factor. When the selectivity of the glass is higher than 2, it gives you twice as much light versus heat.

KEY PERFORMANCE FACTORS



Light transmission (LT)

Percentage of visible light directly transmitted through the glass.



Reflection outside (LRe)

Percentage of visible light directly reflected from the exterior glass surface.



Reflection inside (LRi)

Percentage of visible light directly reflected from the interior glass surface.



Color rendering index

Ability of the glass to keep the colors the same as if they were observed without glazing. Measured with a scale from 1 to 100. A low CRI gives a poor representation of colors, and a high CRI gives a natural and bright representation of colors.



Ug-value

Measure of the heat loss by penetration of the glass. The lower the Ug-value is, the better the insulating properties are. Expressed in W/m^2K .

GLASS TECHNOLOGY FOR SUSTAINABLE HABITAT

Saint-Gobain Building Glass offers a complete range of energy efficient coated glass and insulated glazing. With solar control, low emissivity, low maintenance and transparency, our glass meets the requirements of low energy consumption buildings.

The technology behind solar control and low emissivity is a thin transparent coating of metallic oxides, deposited on one or two glass panes of a double or triple glazing unit. Invisible thermal shield, this coating retains the heat inside the building and captures the sun heat to keep it outside.

The innovation and the technology developed by Saint-Gobain serve comfort and well-being for sustainable habitat.

KEY ASSETS



Protection from the sun heat: Solar Control Glass

Solar control glass reduce overheating within buildings whilst letting the daylight in.



Protection from the cold: Low-E Glass

Double or triple glazing significantly reduces heat loss to the exterior, reducing the energy usage for internal heating.



Easy maintenance - BIOCLEAN®

BIOCLEAN® reduces the required cleaning frequency of glazing, and also reduces the occurrence of external condensation.



Total transparency: Anti-reflective glass

Anti-reflective glass is a key asset, especially for shop front projects, where reflections on glass must not block the visibility of products.

HOW TO READ OUR PRODUCT NAMES

COOL-LITE® XTREME Extremely selective solar control (triple silver) with reinforced thermal insulation

COOL-LITE® XTREME 70/33 II

Performance	Light Transmission (TL)	g-value/solar factor	Processing
XTREME = Extremely selective solar control coatings (triple silver) with reinforced thermal insulation	in double glass unit with 6 16 4 mm	in double glass unit with 6 16 4 mm	II = to-be-tempered
			ø = annealed

COOL-LITE® SKN COOL-LITE® K COOL-LITE® ST Highly selective solar control (double silver) with reinforced thermal insulation Selective solar control coatings (single silver) with thermal insulation

Standard solar control coatings offering full flexibility for processing

COOL-LITE® SKN 183 II

Performance	Color	Substrate	Light Transmission (TL)	Processing
S = selective	B = blue	O = DIAMANT®	at 6 mm mono pane	II = to-be-tempered
K = K-value (Ug-value)	G = golden	1 = PLANICLEAR®		ø = annealed
	N = neutral	2 = PARSOL® Bronze		
	S = silver	3 = PARSOL® Grey		
		4 = PARSOL® Green		
	T = temperable	7 = PARSOL® Saphire blue		

2 / SAINT-GOBAIN BUILDING GLASS - FACADE SAINT-GOBAIN BUILDING GLASS - FACADE /3

EASYPRO®

EASYPRO® is a revolutionary and unique temporary surface protection developed and offered exclusively by Saint-Gobain. Deposited on to-be-tempered coated glass, it delivers effective protection against mechanical damage as well as ageing, during transport and processing, from deposition of the coating until tempering. During tempering, EASYPRO® simply burns off without leaving any residue inside or outside the furnace and without any negative impact on the environment or personal health and safety.

Developped for the ease of processing, EASYPRO® offers flexibility and productivity

- EASYPRO® protects the coating so there
 is a reduced risk of surface scratches when
 transporting the glass and also increase the
 shelf life of coated glass on stock or cut
 offering more flexibility.
- EASYPRO® help to save time and money by eliminating time to unseal packs and dispose plastic waste. This also reduces the risk of injury associated with this activity. There is also significant gain in productivity due to tempering cycle times being reduced with EASYPRO®. Internal waste can be significantly improved and quality issues can be reduced.



EASYPRO® is a sustainable innovation, minimizing waste and saving energy

- This protective layer not only reduces the amount of packaging used during transportation to protect the glass but as well facilitates loading into trucks, and reduces the carbon footprint during transport.
- It reduces the scraps and damages, thus improving industrial performance during glass processing and generating less waste.
- EASYPRO® offers energy saving benefits by allowing reduced temperature levels in the furnace.



EASYPRO® is also an ally for ambitious architectural projects and helps to preserve the aesthetic and performance of the coated glass after tempering

- EASYPRO® contributes considerably to the improvement of the quality of glass after tempering, and participates to the reduction of anisotropy. EASYPRO® helps not to have to compromise between the quality and the productivity
- EASYPRO® on Saint-Gobain solar control coatings guarantees to deliver the most performant glass with optimal aesthetics for the most demanding projects, such as those that boast impressive Overlenght large span glass.



EASYPRO® protects today the following tobe-tempered coatings (on PLANICLEAR® and DIAMANT®):

- COOL-LITE® XTREME II (standard with EASYPRO®, except XTREME SILVER II)
- COOL-LITE® SKN II and KN II (standard with EASYPRO®)
- EASYPRO® is also available on demand on some PLANITHERM® II glass for thicknesses from 4 mm to 12 mm. Please check with your local sales team. (Subject to change)

OVERLENGTH

To answer a major trend in architecture, we think big. Our large-scale range now includes glass panes with dimensions up to:

18 x 3,21 m

The benefits are revolutionary:

- greater design possibilities,
- spectacular optical highlights,
- larger evenly shaped facades,
- panoramic views while benefiting from a high performance glazing.

Coatings available, on DIAMANT® or PLANICLEAR® (in 8, 10 and 12 mm):

- PLANITHERM® II.
- COOL-LITE® SKN II
- COOL-LITE® XTREME II

The glass can be heat-treated, laminated, and processed as multifunctional Insulated Glass Units (IGU) (double Glazed Units (DGU) or triple Glazed Units (TGU).

Contact us for individual inquiries. (Subject to change)









4 / SAINT-GOBAIN BUILDING GLASS - FACADE SAINT-GOBAIN BUILDING GLASS - FACADE /5

Double Glazing Units - CLIMAPLUS®

	coating		Politic					and a street			assessed			processing p	possibilities	
		color in		solar factor	shading coefficient	selectivity	reflection outside	reflection inside	Ug-value ²	weight [kg/m²]	sound reduc- tion index	use as mono glazing		lamination		screen-
	to be tempered / annealed	reflection	LT ¹ [%]	g-value ¹	SC	LT/g	LRe [%]	LRi [%]	[W/m²K]	[kg/m²]	Rw,P (C, Ctr) ³ [dB]	(coating on #2)	tempering			printing & enamelling ⁶
ر ا	Extremely selective solar control coating with rein	forced therma	al insulation				1								'	





COOL-LITE® XTREME in double glazing unit CLIMAPLUS® (6 | 16 | 4 mm, 90% Argon, coating on face #2) on PLANICLEAR® or DIAMANT® Values given according to the standards IEN 410, IEN 673 and IEN 12758

values given according to the standards Enviro, i	_IN 0/5 dild LIN	12750										
COOL-LITE® XTREME 70/33 II DIAMANT® with EASYPRO®	extra neutral	71	0.33	0.38	2.15	11	13	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁵
COOL-LITE® XTREME 70/33 DIAMANT®	extra neutral	71	0.33	0.38	2.15	11	13	1.0	25.0	35(-1;-5)		
COOL-LITE® XTREME 70/33 II with EASYPRO®	neutral	70	0.33	0.38	2.12	11	13	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁵
COOL-LITE® XTREME 70/33	neutral	70	0.33	0.38	2.12	11	13	1.0	25.0	35(-1;-5)		
NEW COOL-LITE® XTREME 61/29 II DIAMANT® with EASYPRO®	extra neutral	62	0.29	0.33	2.14	11	15	1.0	25.0	35(-1;-5)	to be tempered	
NEW COOL-LITE® XTREME 61/29 DIAMANT®	extra neutral	62	0.29	0.33	2.14	11	14	1.0	25.0	35(-1;-5)		
NEW COOL-LITE® XTREME 61/29 II with EASYPRO®	neutral	61	0.29	0.33	2.10	11	15	1.0	25.0	35(-1;-5)	to be tempered	
NEW COOL-LITE® XTREME 61/29	neutral	61	0.29	0.33	2.10	11	14	1.0	25.0	35(-1;-5)		
COOL-LITE® XTREME SILVER II DIAMANT®	bright silver	50	0.25	0.29	2.00	30	18	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁵
COOL-LITE® XTREME SILVER II	Silver	49	0.25	0.29	1.96	30	18	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁵
COOL-LITE® XTREME 50/22 II DIAMANT® with EASYPRO®	extra neutral	48	0.21	0.24	2.29	16	18	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁵
COOL-LITE® XTREME 50/22 II with EASYPRO®	neutral	47	0.21	0.24	2.24	16	18	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁵





Highly selective solar control coating with reinforced thermal insulation COOL-LITE® SKN in double glazing unit CLIMAPLUS® (6 | 16 | 4 mm, 90% Argon, coating on face #2) on PLANICLEAR® or DIAMANT® Values given according to the standards ¹EN 410, ²EN 673 and ³EN 12758

COOL-LITE® SKN 083 II with EASYPRO®	extra neutral	76	0.41	0.47	1.85	12	13	1.0	25.0	35(-1;-5)	to be tempered		Yes ⁵
COOL-LITE® SKN 083	extra neutral	76	0.41	0.47	1.85	12	13	1.0	25.0	35(-1;-5)			
COOL-LITE® SKN 183 II with EASYPRO®	neutral	75	0.40	0.46	1.88	12	13	1.0	25.0	35(-1;-5)	to be tempered		Yes ⁵
COOL-LITE® SKN 183	neutral	75	0.40	0.46	1.88	12	13	1.0	25.0	35(-1;-5)			
COOL-LITE® SKN 076 II with EASYPRO®	extra neutral	71	0.38	0.44	1.87	13	15	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 076	extra neutral	71	0.38	0.44	1.87	13	15	1.0	25.0	35(-1;-5)			
COOL-LITE® SKN 176 II with EASYPRO®	neutral	70	0.37	0.43	1.89	13	15	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 176	neutral	70	0.37	0.43	1.89	13	15	1.0	25.0	35(-1;-5)			
COOL-LITE® SKN 065 II with EASYPRO®	extra neutral	62	0.35	0.40	1.77	17	19	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 065	extra neutral	62	0.35	0.40	1.77	17	18	1.0	25.0	35(-1;-5)		Yes ⁸	
COOL-LITE® SKN 165 II with EASYPRO®	neutral	61	0.34	0.39	1.79	16	19	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 165	neutral	61	0.34	0.39	1.79	16	18	1.0	25.0	35(-1;-5)		Yes ⁸	
COOL-LITE® SKN 054 II with EASYPRO®	extra neutral	53	0.29	0.33	1.83	18	23	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 054	extra neutral	53	0.29	0.33	1.83	19	22	1.0	25.0	35(-1;-5)		Yes ⁸	
COOL-LITE® SKN 154 II with EASYPRO®	neutral	52	0.28	0.32	1.85	18	23	1.0	25.0	35(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 154	neutral	52	0.28	0.32	1.85	19	22	1.0	25.0	35(-1;-5)		Yes ⁸	
COOL-LITE® SKN 045	neutral	42	0.22	0.25	1.91	19	15	1.1	25.0	35(-1;-5)			
COOL-LITE® SKN 145	neutral	41	0.22	0.25	1.86	19	15	1.1	25.0	35(-1;-5)			
COOL-LITE® SKN 044 II with EASYPRO®	extra neutral	43	0.23	0.27	1.87	21	15	1.1	25.0	35(-1;-5)	to be tempered	Yes ⁸	
COOL-LITE® SKN 144 II with EASYPRO®	neutral	42	0.23	0.26	1.83	20	15	1.1	25.0	35(-1;-5)	to be tempered	Yes ⁸	

⁴ Solar control coating in contact with PVB modifies performances and aesthetics. Please contact us to get the approved list.

⁵ Bending results depend on the process/technology used, trials should be done for validation. 6 Screen-printing/roller coating/spray/digital printing inks and enamels validation is required.

⁷ COOL-LITE® SKN 154 may have a slight color deviation in transmission compared to SKN 154 II. Validation by Mock-up is recommended if both versions are used on the same facade.

8 This coating can be laminated for use on a facade up to 1.500m² and project must be made from a single production batch from SGG.

Double Glazing Units - CLIMAPLUS®

	coating		Polit								assessed			processing	possibilities	
	to be tempered / annealed	color in reflection	light transmission LT¹ [%]	solar factor g-value ¹	shading coefficient SC	selectivity LT / g	reflection outside LRe [%]	reflection inside LRi [%]	Ug-value² [W/m²K]	weight [kg/m²]	sound reduc- tion index Rw,P (C, Ctr) ³ [dB]	glazing	tempering	lamination tested to- wards PVB ⁴	bending⁵	screen- printing & enamelling ⁶
\ <u>\</u>	Selective solar control coating with reinforced the	ermal insulatio	n													





COOL-LITE® K in double glazing unit CLIMAPLUS® (6 | 16 | 4 mm, 90% Argon, coating on face #2) on PLANICLEAR®

/alues given according to the standards ¹EN 410, ²EN 673 and ³EN 12758

COOL-LITE® KN 166 II with EASYPRO® neutral	01	0.39	0.45	1.56	22	26	1.0	25.0	35(-1;-5)	to be tempered	
NEW COOL-LITE® KN 148 II with EASYPRO® neutral	47	0.32	0.37	1.47	27	18	1.0	25.0	35(-1;-5)	to be tempered	





Selective solar control coating with thermal insulation

COOL-LITE® K in double glazing unit CLIMAPLUS® (6 | 16 | 4 mm, 90% Argon, coating on face #2 with PLANITHERM® XN on face #3) on PLANICLEAR® Values given according to the standards ¹EN 410, ²EN 673 and ³EN 12758

COOL-LITE® KG 137 tempered	golden	34	0.28	0.32	1.21	33	28	1.1	25.0	35(-1;-5)	to be tempered		
COOL-LITE® KG 137 annealed	golden	35	0.27	0.31	1.30	30	25	1.1	25.0	35(-1;-5)			
COOL-LITE® KNT 164	neutral	58	0.42	0.49	1.38	13	7	1.1	25.0	35(-1;-5)	temperable	Yes	
COOL-LITE® KNT 155	neutral	48	0.35	0.44	1.37	16	7	1.1	25.0	35(-1;-5)	temperable	Yes	
COOL-LITE® KNT 140	neutral	38	0.27	0.31	1.41	22	9	1.1	25.0	35(-1;-5)	temperable	Yes	
COOL-LITE® KS 147	silver	43	0.30	0.34	1.26	42	34	1.1	25.0	35(-1;-5)			
NEW COOL-LITE® KS 146 II	silver	43	0.29	0.33	1.48	33	16	1.1	25.0	35 (-1;-5)	to be tempered		
COOL-LITE® KS 138 II	silver	37	0.25	0.29	1.48	38	17	1.1	25.0	35(-1;-5)	to be tempered		





Solar control glass offering full flexibility for processing COOL-LITE® ST in double glazing unit CLIMAPLUS® (6 | 16 | 4 mm, 90% Argon, coating on face #2 with PLANITHERM® XN on face #3) on PLANICLEAR® Values given according to the standards ¹EN 410, ²EN 673 and ³EN 12758

COOL-LITE® ST BRIGHT SILVER DIAMANT®	silver	63	0.52	0.60	1.21	32	31	1.1	25.0	35(-1;-5)	Yes	temperable	Yes	Yes ⁵ .	Yes
COOL-LITE® ST BRIGHT SILVER	silver	61	0.51	0.58	1.20	32	31	1.1	25.0	35(-1;-5)	Yes	temperable	Yes	Yes ⁵	Yes
COOL-LITE® ST 167	neutral	61	0.49	0.56	1.24	21	21	1.1	25.0	35(-1;-5)	Yes	temperable	Yes	Yes ⁵	Yes
COOL-LITE® ST 150	neutral	46	0.38	0.44	1.21	19	19	1.1	25.0	35(-1;-5)	Yes	temperable	Yes	Yes ⁵	Yes
COOL-LITE® ST 136	grey	34	0.28	0.32	1.21	23	20	1.1	25.0	35(-1;-5)	Yes	temperable	Yes		Yes
COOL-LITE® ST 120	silver	19	0.17	0.20	1.12	32	26	1.1	25.0	35(-1;-5)	Yes	temperable	Yes		Yes
COOL-LITE® STB 136	blue	33	0.28	0.32	1.18	19	17	1.1	25.0	35(-1;-5)	Yes	temperable	Yes		Yes
COOL-LITE® STB 120	blue	20	0.18	0.21	1.11	21	29	1.1	25.0	35(-1;-5)	Yes	temperable	Yes		Yes



Low-E coating in double glazing unit CLIMAPLUS® (4 | 16 | 4 mm, 90% Argon, coating on face #3) on PLANICLEAR® or DIAMANT®

Values given according to the standards 'EN 410, 'EN 6/3 a	nd ³ EN 12/58											
PLANITHERM® XN II DIAMANT® (with EASYPRO® on demand)	extra neutral	83	0.67	0.77	1.24	12	12	1.1	20.0	31(-1;-4)	to be tempered	Yes ⁵
PLANITHERM® XN DIAMANT®	extra neutral	83	0.67	0.77	1.24	12	12	1.1	20.0	31(-1;-4)		
PLANITHERM® XN II (with EASYPRO® on demand)	neutral	82	0.65	0.75	1.26	12	12	1.1	20.0	31(-1;-4)	to be tempered	Yes ⁵
PLANITHERM® XN	neutral	82	0.65	0.75	1.26	11	12	1.1	20.0	31(-1;-4)		
PLANITHERM® ONE II DIAMANT® (with EASYPRO® on demand)	extra neutral	73	0.54	0.62	1.35	22	22	1.0	20.0	31(-1;-4)	to be tempered	Yes ⁵
PLANITHERM® ONE DIAMANT®	extra neutral	73	0.53	0.61	1.38	23	23	1.0	20.0	31(-1;-4)		
PLANITHERM® ONE II (with EASYPRO® on demand)	neutral	72	0.53	0.61	1.36	22	23	1.0	20.0	31(-1;-4)	to be tempered	Yes ⁵
PLANITHERM® ONE	neutral	72	0.52	0.60	1.38	22	23	1.0	20.0	31(-1;-4)		

⁴ Solar control coating in contact with PVB modifies performances and aesthetics. Please contact us to get the approved list. 5 Bending results depend on the process/technology used; trials should be done for validation. 6 Screen-printing/roller coating/spray/digital printing inks and enamels validation is required.

Double Glazing Units - CLIMAPLUS®

	coating		limba				un filmation	us floories			assessed			processing p	ossibilities	
	to be tempered / annealed	color in reflection	light transmission LT ¹ [%]	solar factor g-value ¹	shading coefficient SC	selectivity LT / g	reflection outside LRe [%]	reflection inside LRi [%]	Ug-value² [W/m²K]	weight [kg/m²]	sound reduc- tion index Rw,P (C, Ctr) ³ [dB]	use as mono glazing (coating on #2)		lamination tested to- wards PVB ⁴	bending⁵	screen- printing & enamelling ⁶
***	Low-E coating in double glazing unit CLIMAPLUS® (4 16 Values given according to the standards ¹EN 410, ²EN 673 and		rgon, coating (on face #3) on	PLANICLEAR	® or DIAMANT	* ®									
	ECLAZ® II DIAMANT®	extra neutral	84	0.73	0.83	1.15	12	12	1.1	20.0	31(-1;-4)		to be tempered			
	ECLAZ® DIAMANT®	extra neutral	85	0.73	0.84	1.16	12	12	1.1	20.0	31(-1;-4)					
	ECLAZ® II	neutral	83	0.71	0.81	1.17	12	11	1.1	20.0	31(-1;-4)		to be tempered			
	ECLAZ®	neutral	83	0.71	0.81	1.17	12	11	1.1	20.0	31(-1;-4)					
	ECLAZ® ONE II DIAMANT®	extra neutral	80	0.61	0.71	1.31	16	18	1.0	20.0	31(-1;-4)		to be tempered			
	ECLAZ® ONE DIAMANT®	extra neutral	81	0.62	0.71	1.31	15	16	1.0	20.0	31(-1;-4)					
	ECLAZ® ONE II	neutral	79	0.60	0.69	1.32	16	18	1.0	20.0	31(-1;-4)		to be tempered			
	ECLAZ® ONE	neutral	80	0.60	0.69	1.33	15	16	1.0	20.0	31(-1;-4)					



BIOCLEAN® in double glazing unit CLIMAPLUS® (6 | 16 | 4 mm, 90% Argon) on PLANICLEAR® for easy maintenance Values given according to the standards ¹EN 410, ²EN 673 and ³EN 12758

BIOCLEAN® II	neutral	79	0.76	0.87	1.04	18	18	2.6	25.0	35(-1;-5)	to be tempered	
BIOCLEAN®	neutral	77	0.74	0.85	1.04	17	17	2.6	25.0	35(-1;-5)		
NEW BIOCLEAN® XTREME 61/29	neutral	57	0.27	0.31	2.11	14	15	1.0	25.0	35(-1;-5)		
BIOCLEAN® SKN 183	neutral	70	0.37	0.43	1.89	15	15	1.0	25.0	35(-1;-5)		
BIOCLEAN® SKN 176	neutral	66	0.35	0.40	1.89	16	17	1.0	25.0	35(-1;-5)		
BIOCLEAN® SKN 165	neutral	57	0.32	0.37	1.78	19	19	1.0	25.0	35(-1;-5)		
BIOCLEAN® SKN 154	neutral	49	0.26	0.30	1.88	21	23	1.0	25.0	35(-1;-5)		
BIOCLEAN® SKN 145	neutral	39	0.21	0.24	1.86	21	16	1.1	25.0	35(-1;-5)		

⁴ Solar control coating in contact with PVB modifies performances and aesthetics. Please contact us to get the approved list. 5 Bending results depend on the process/ technology used; trials should be done for validation. 6 Screen-printing/roller coating/spray/digital printing inks and enamels validation is required.

Manalithia and Laminated Class

coating to be tempered / annealed	color in reflection	light transmission LT ¹ [%]	solar factor g-value ¹	shading coefficient SC	selectivity LT / g	reflection outside LRe [%]	reflection inside LRi [%]	Ug-value² [W/m²K]	weight [kg/m²]	assessed sound reduc- tion index Rw,P (C, Ctr) ³ [dB]	Description / processing possibilities
VISION-LITE® on DIAMANT® for anti-reflectance (STADIP® Values given according to the standards ¹ EN 410, ² EN 673 ar		lass) and Mono	lithic glass)								

STADIP® VISION-LITE® (laminated glass 44.2) DIAMANT®	extra neutral	97	0.84	0.97	1.15	1	1	5.5	20.0	34(-1;-2)	VISION-LITE coating on faces #1 and #4 of laminated glass
VISION-LITE® II DIAMANT® (6 mm)	extra neutral	98	0.87	0.99	1.13	1	1	5.7	15.0	32(-1;-2)	VISION-LITE coating on both sides (#1 & #2) of monolithic glass - to be tempered
Semi VISION-LITE® II DIAMANT® (6 mm)	extra neutral	94	0.88	1.01	1.07	5	5	5.7	15.0	32(-1;-2)	VISION-LITE coating on one side of the glass - to be tempered / to be laminated
Semi VISION-LITE® DIAMANT® (6 mm)	extra neutral	94	0.89	1.03	1.06	5	5	5.7	15.0	32(-1;-2)	VISION-LITE coating on one side of the glass - to be laminated

10/ SAINT-GOBAIN BUILDING GLASS - FACADE SAINT-GOBAIN BUILDING GLASS - FACADE /11

Triple Glazing Units - CLIMATOP®

coating		Parks								assessed			processing	possibilities	
to be tempered / annealed	color in reflection	light transmission LT ¹ [%]	solar factor g-value ¹	shading coefficient SC	selectivity LT / g	reflection outside LRe [%]	reflection inside LRi [%]	Ug-value² [W/m²K]	weight [kg/m²]	sound reduc- tion index Rw,P (C, Ctr) ³ [dB]	use as mono glazing (coating on #2)	tempering	lamination tested to- wards PVB ⁴		screen- printing & enamelling ⁶





Extremely selective solar control coating with reinforced thermal insulation COOL-LITE® XTREME in triple glazing unit CLIMATOP® (6 | 12 | 4 | 12 | 4 mm, 90% Argon, coating on face #2 with PLANITHERM® XN on face #5) on PLANICLEAR® or DIAMANT® Values given according to the standards ¹EN 410, ²EN 673 and ³EN 12758

values given according to the standards EN 410,	LIN 0/3 allu "LIN	12/30											
COOL-LITE® XTREME 70/33 II DIAMANT® with EASYPRO®	extra neutral	65	0.31	0.36	2.10	13	16	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁵	
COOL-LITE® XTREME 70/33 DIAMANT®	extra neutral	65	0.31	0.36	2.10	13	16	0.7	35.0	36(-1;-5)			
COOL-LITE® XTREME 70/33 II with EASYPRO®	neutral	63	0.31	0.35	2.03	13	16	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁵	
COOL-LITE® XTREME 70/33	neutral	63	0.31	0.35	2.03	13	16	0.7	35.0	36(-1;-5)			
NEW COOL-LITE® XTREME 61/29 II DIAMANT® with EASYPRO®	extra neutral	57	0.28	0.32	2.04	13	18	0.7	35.0	36(-1;-5)	to be tempered		
NEW COOL-LITE® XTREME 61/29 DIAMANT®	extra neutral	57	0.28	0.32	2.04	13	17	0.7	35.0	36(-1;-5)			
NEW COOL-LITE® XTREME 61/29 II with EASYPRO®	neutral	55	0.27	0.31	2.04	13	17	0.7	35.0	36(-1;-5)	to be tempered		
NEW COOL-LITE® XTREME 61/29	neutral	55	0.27	0.31	2.04	13	16	0.7	35.0	36(-1;-5)			
COOL-LITE® XTREME SILVER II DIAMANT®	bright silver	46	0.24	0.27	1.92	31	20	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁵	
COOL-LITE® XTREME SILVER II	Silver	45	0.23	0.27	1.96	30	20	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁵	
COOL-LITE® XTREME 50/22 II DIAMANT® with EASYPRO®	extra neutral	44	0.20	0.23	2.20	17	20	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁵	
COOL-LITE® XTREME 50/22 II with EASYPRO®	neutral	43	0.19	0.22	2.26	17	20	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁵	





Highly selective solar control coating with reinforced thermal insulation COOL-LITE® SKN in triple glazing unit CLIMATOP® (6 | 12 | 4 | 12 | 4 mm, 90% Argon, coating on face #2 with PLANITHERM® XN on face #5) on PLANICLEAR® or DIAMANT® Values given according to the standards IEN 410, IEN 673 and IEN 12758

COOL-LITE® SKN 083 II with EASYPRO®	extra neutral	69	0.38	0.44	1.82	15	16	0.7	35.0	36(-1;-5)	to be tempered		Yes ⁵
COOL-LITE® SKN 083	extra neutral	69	0.38	0.44	1.82	15	16	0.7	35.0	36(-1;-5)			
COOL-LITE® SKN 183 II with EASYPRO®	neutral	68	0.37	0.43	1.84	14	16	0.7	35.0	36(-1;-5)	to be tempered		Yes ⁵
COOL-LITE® SKN 183	neutral	68	0.37	0.43	1.84	14	16	0.7	35.0	36(-1;-5)			
COOL-LITE® SKN 076 II with EASYPRO®	extra neutral	65	0.35	0.37	1.86	15	18	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 076	extra neutral	65	0.35	0.41	1.86	15	18	0.7	35.0	36(-1;-5)			
COOL-LITE® SKN 176 II with EASYPRO®	neutral	64	0.34	0.40	1.88	15	17	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 176	neutral	64	0.34	0.40	1.88	15	17	0.7	35.0	36(-1;-5)			
COOL-LITE ®SKN 065 II with EASYPRO®	extra neutral	57	0.32	0.37	1.78	18	21	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 065	extra neutral	57	0.32	0.37	1.78	18	20	0.7	35.0	36(-1;-5)		Yes ⁸	
COOL-LITE® SKN 165 II with EASYPRO®	neutral	55	0.31	0.36	1.77	18	20	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 165	neutral	55	0.32	0.36	1.72	18	20	0.7	35.0	36(-1;-5)		Yes ⁸	
COOL-LITE® SKN 054 II with EASYPRO®	extra neutral	49	0.27	0.31	1.81	19	24	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LIT®E SKN 054	extra neutral	49	0.27	0.31	1.81	20	24	0.7	35.0	36(-1;-5)		Yes ⁸	
COOL-LITE® SKN 154 II with EASYPRO®	neutral	47	0.26	0.30	1.81	19	23	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁸	Yes ⁵
COOL-LITE® SKN 154	neutral	47	0.26	0.30	1.81	20	23	0.7	35.0	36(-1;-5)		Yes ⁸	
COOL-LITE® SKN 045	neutral	38	0.21	0.24	1.81	20	18	0.7	35.0	36(-1;-5)			
COOL-LITE® SKN 145	neutral	37	0.20	0.23	1.85	20	17	0.7	35.0	36(-1;-5)			
COOL-LITE® SKN 044 II with EASYPRO®	extra neutral	39	0.21	0.25	1.86	22	18	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁸	
COOL-LITE® SKN 144 II with EASYPRO®	neutral	38	0.21	0.24	1.81	21	17	0.7	35.0	36(-1;-5)	to be tempered	Yes ⁸	

⁴ Solar control coating in contact with PVB modifies performances and aesthetics. Please contact us to get the approved list. 5 Bending results depend on the process/technology used; trials should be done for validation. 6 Screen-printing/roller coating/spray/digital printing inks and enamels validation is required.

⁷ COOL-LITE® SKN 154 may have a slight color deviation in transmission compared to SKN 154 II. Validation by Mock-up is recommended if both versions are used on the same facade.

8 This coating can be laminated for use on a facade up to 1.500m² and project must be made from a single production batch from SGG.

Triple Glazing Units - CLIMATOP®

coating		light				reflection	reflection			assessed			processing	possibilities	
to be tempered / annealed	color in reflection	transmission LT ¹ [%]	solar factor g-value ¹	shading coefficient SC	selectivity LT / g	outside LRe [%]	inside LRi [%]	Ug-value² [W/m²K]	weight [kg/m²]	sound reduc- tion index	use as mono glazing coating on #2)		lamination tested to- wards PVB ⁴	bending⁵	screen- printing enamellin
Selective solar control coating with reinforced the COOL-LITE® K in triple glazing unit CLIMATOP® (6 Values given according to the standards IEN 410, 2E	6 12 4 12 4	mm, 90% Arg	on, coating on	ı face #2 with	PLANITHERM®	XN on face #	5) on PLANICL	.EAR®							
COOL-LITE® KN 166 II with EASYPRO®	neutral	55	0.35	0.40	1.57	23	26	0.7	35.0	36(-1;-5)		to be tempered			
NEW COOL-LITE® KN 148 II with EASYPRO®	neutral	43	0.28	0.32	1.54	28	20	0.7	35.0	36(-1;-5)		to be tempered			
Selective solar control coating with thermal insula	ation														
Selective solar control coating with thermal insular COOL-LITE® K in triple glazing unit CLIMATOP® (6 Values given according to the standards EN 410, 2E COOL-LITE® KG 137 tempered	6 12 4 12 4		on, coating on	0.28	PLANITHERM®	XN on face #	3 and #5) on F	PLANICLEAR®	35.0	36(-1;-5)	_	to-be-tempered		_	
COOL-LITE® K in triple glazing unit CLIMATOP® (6 Values given according to the standards ¹EN 410, ²E	6 12 4 12 4 EN 673 and ³ EN	l 12758							35.0 35.0	36(-1;-5) 36(-1;-5)		to-be-tempered			
COOL-LITE® K in triple glazing unit CLIMATOP® (6 Values given according to the standards ¹EN 410, ²E COOL-LITE® KG 137 tempered	6 12 4 12 4 EN 673 and ³ EN golden	1 12758 31	0.24	0.28	1.29	33	28	0.7				to-be-tempered temperable	Yes		
COOL-LITE® K in triple glazing unit CLIMATOP® (6 Values given according to the standards ¹EN 410, ²E COOL-LITE® KG 137 tempered COOL-LITE® KG 137 annealed COOL-LITE® KNT 164	6 12 4 12 4 EN 673 and ³ EN golden golden	31 31	0.24	0.28	1.29	33 30	28 26	0.7	35.0	36(-1;-5)			Yes Yes		
COOL-LITE® K in triple glazing unit CLIMATOP® (6 Values given according to the standards ¹EN 410, ²E COOL-LITE® KG 137 tempered COOL-LITE® KG 137 annealed COOL-LITE® KNT 164 COOL-LITE® KNT 155	6 12 4 12 4 EN 673 and ³ EN golden golden neutral	31 31 52	0.24 0.24 0.37	0.28 0.28 0.42	1.29 1.29 1.41	33 30 14	28 26 11	0.7 0.7 0.7	35.0 35.0	36(-1;-5) 36(-1;-5)		temperable			
COOL-LITE® K in triple glazing unit CLIMATOP® (6 Values given according to the standards ¹EN 410, ²E COOL-LITE® KG 137 tempered COOL-LITE® KG 137 annealed COOL-LITE® KNT 164 COOL-LITE® KNT 155 COOL-LITE® KNT 140	6 12 4 12 4 EN 673 and ³ EN golden golden neutral	31 31 52 43	0.24 0.24 0.37 0.30	0.28 0.28 0.42 0.35	1.29 1.29 1.41 1.43	33 30 14 17	28 26 11	0.7 0.7 0.7 0.7	35.0 35.0 35.0	36(-1;-5) 36(-1;-5) 36(-1;-5)		temperable temperable	Yes		
COOL-LITE® K in triple glazing unit CLIMATOP® (6	6 12 4 12 4 EN 673 and ³ EN golden golden neutral neutral	31 31 52 43 34	0.24 0.24 0.37 0.30 0.24	0.28 0.28 0.42 0.35 0.27	1.29 1.29 1.41 1.43 1.42	33 30 14 17 23	28 26 11 11 12	0.7 0.7 0.7 0.7	35.0 35.0 35.0 35.0	36(-1;-5) 36(-1;-5) 36(-1;-5)		temperable temperable	Yes		





Solar control glass offering full flexibility for processing COOL-LITE® ST in triple glazing unit CLIMATOP® (6 | 12 | 4 | 12 | 4 mm, 90% Argon, coating on face #2, with PLANITHERM® XN on face #3 and #5) on PLANICLEAR® Values given according to the standards ¹EN 410, ²EN 673 and ³EN 12758

COOL-LITE® ST BRIGHT SILVER DIAMANT®	silver	58	0.45	0.52	1.29	34	31	0.7	35.0	36(-1;-5)	Yes	temperable	Yes	Yes ⁵	Yes
COOL-LITE® ST BRIGHT SILVER	silver	56	0.44	0.50	1.27	33	30	0.7	35.0	36(-1;-5)	Yes	temperable	Yes	Yes ⁵	Yes
COOL-LITE® ST 167	neutral	55	0.42	0.48	1.31	22	22	0.7	35.0	36(-1;-5)	Yes	temperable	Yes	Yes ⁵	Yes
COOL-LITE® ST 150	neutral	42	0.33	0.37	1.27	20	21	0.7	35.0	36(-1;-5)	Yes	temperable	Yes	Yes ⁵	Yes
COOL-LITE® ST 136	grey	31	0.24	0.27	1.29	23	21	0.7	35.0	36(-1;-5)	Yes	temperable	Yes		Yes
COOL-LITE® ST 120	silver	17	0.15	0.17	1.13	32	27	0.7	35.0	36(-1;-5)	Yes	temperable	Yes		Yes
COOL-LITE® STB 136	blue	30	0.24	0.27	1.25	19	19	0.7	35.0	36(-1;-5)	Yes	temperable	Yes		Yes
COOL-LITE® STB 120	blue	18	0.15	0.18	1.20	21	29	0.7	35.0	36(-1;-5)	Yes	temperable	Yes		Yes



Low-E coating in triple glazing unit CLIMATOP® (4 | 12 | 4 | 12 | 4 mm, 90% Argon, coating on face #2, with PLANITHERM® XN on face #5) on PLANICLEAR® or DIAMANT® Values given according to the standards IEN 410, IEN 673 and IEN 12758

PLANITHERM® XN II DIAMANT® (with EASYPRO® on demand)	extra neutral	76	0.56	0.64	1.36	15	15	0.7	30.0	32(-1;-5)	to be tempered	Yes ⁵
PLANITHERM® XN DIAMANT®	extra neutral	76	0.56	0.64	1.36	15	15	0.7	30.0	32(-1;-5)		
PLANITHERM® XN II (with EASYPRO® on demand)	neutral	74	0.54	0.62	1.37	14	14	0.7	30.0	32(-1;-5)	to be tempered	Yes ⁵
PLANITHERM® XN	neutral	74	0.54	0.62	1.37	14	14	0.7	30.0	32(-1;-5)		
PLANITHERM® ONE II DIAMANT® (with EASYPRO® on demand)	extra neutral	67	0.47	0.54	1.43	26	24	0.7	30.0	32(-1;-5)	to be tempered	Yes ⁵
PLANITHERM® ONE DIAMANT®	extra neutral	67	0.45	0.52	1.49	26	24	0.7	30.0	32(-1;-5)		
PLANITHERM® ONE II (with EASYPRO® on demand)	neutral	65	0.45	0.52	1.44	25	23	0.7	30.0	32(-1;-5)	to be tempered	Yes ⁵
PLANITHERM® ONE	neutral	65	0.44	0.50	1.48	25	23	0.7	30.0	32(-1;-5)		

⁴ Solar control coating in contact with PVB modifies performances and aesthetics. Please contact us to get the approved list. 5 Bending results depend on the process/ technology used; trials should be done for validation. 6 Screen-printing/ roller coating/ spray/ digital printing inks and enamels validation is required.

14/ SAINT-GOBAIN BUILDING GLASS - FACADE SAINT-GOBAIN BUILDING GLASS - FACADE /15

Triple Glazing Units - CLIMATOP®

coating	color in reflection	Polit				and the street	na Chankian			assessed			processing	possibilities	
to be tempered / annealed		light transmission LT¹ [%]	solar factor g-value ¹	shading coefficient SC	selectivity LT / g	reflection outside LRe [%]	reflection inside LRi [%]	Ug-value² [W/m²K]	weight [kg/m²]	sound reduc- tion index Rw,P (C, Ctr) ³ [dB]	use as mono glazing (coating on #2)	tempering	lamination tested to- wards PVB ⁴	bending⁵	screen- printing & enamelling ⁶

Low-E coating in triple glazing unit CLIMATOP® (4 | 12 | 4 | 12 | 4 mm, 90% Argon, coating on face #2, with PLANITHERM® XN on face #5) on PLANICLEAR® or DIAMANT® Values given according to the standards ¹EN 410, ²EN 673 and ³EN 12758

ECLAZ® II DIAMANT®	extra neutral	77	0.58	0.66	1.33	14	15	0.7	30.0	32(-1;-5)	to be tempered
ECLAZ® DIAMANT®	extra neutral	77	0.59	0.67	1.31	15	15	0.7	30.0	32(-1;-5)	
ECLAZ® II	neutral	75	0.56	0.64	1.34	14	15	0.7	30.0	32(-1;-5)	to be tempered
ECLAZ®	neutral	76	0.57	0.65	1.33	14	15	0.7	30.0	32(-1;-5)	
ECLAZ® ONE II DIAMANT®	extra neutral	73	0.51	0.58	1.43	20	18	0.7	30.0	32(-1;-5)	to be tempered
ECLAZ® ONE DIAMANT®	extra neutral	74	0.51	0.59	1.45	19	17	0.7	30.0	32(-1;-5)	
ECLAZ® ONE II	neutral	71	0.49	0.57	1.45	20	18	0.7	30.0	32(-1;-5)	to be tempered
ECLAZ® ONE	neutral	72	0.49	0.57	1.47	18	17	0.7	30.0	32(-1;-5)	



BIOCLEAN® in triple glazing unit CLIMATOP® (6 | 12 | 4 | 12 | 4 mm, 90% Argon, with PLANITHERM® XN on face #5) on PLANICLEAR® for easy maintenance Values given according to the standards ¹EN 410, ²EN 673 and ³EN 12758

BIOCLEAN® II	neutral	72	0.57	0.66	1,.26	20	19	1.0	35.0	36(-1;-5)	to be tempered
BIOCLEAN®	neutral	70	0.56	0.64	1.25	20	19	1.0	35.0	36(-1;-5)	
NEW BIOCLEAN® XTREME 61/29	neutral	52	0.25	0.29	2.08	15	17	0.7	35.0	36(-1;-5)	
BIOCLEAN® SKN 183	neutral	64	0.35	0.40	1.83	17	17	0.7	35.0	36(-1;-5)	
BIOCLEAN® SKN 176	neutral	60	0.32	0.37	1.88	17	19	0.7	35.0	36(-1;-5)	
BIOCLEAN® SKN 165	neutral	52	0.30	0.34	1.73	20	21	0.7	35.0	36(-1;-5)	
BIOCLEAN® SKN 154	neutral	45	0.24	0.28	1.88	22	24	0.7	35.0	36(-1;-5)	
BIOCLEAN® SKN 145	neutral	35	0.19	0.22	1.84	22	18	0.7	35.0	36(-1;-5)	

⁴ Solar control coating in contact with PVB modifies performances and aesthetics. Please contact us to get the approved list. 5 Bending results depend on the process/ technology used; trials should be done for validation. 6 Screen-printing/ roller coating/ spray/ digital printing inks and enamels validation is required.

OUR TECHNICAL SUPPORT



Professional high level of service is our priority.

We offer tailor-made advisory about glass products and technical solutions.

Static calculations: deflection and stress calculation are performed for different types of glazing under permanent and variable loads combination.

Thermal stress analysis: calculation of maximum temperatures and analysis of the risks of thermal breakage.

Acoustic calculations: computation of sound transmission loss and calculation acoustic insulation parameters.


Spectrophotometric calculations: the most important glazing parameters such as light transmission, light reflection, energy absorption, Ug, etc.

Daylight analysis and energy simulation: penetration of natural light on the building floor plan or at working plane level.

If you want more information, please contact us at: glass.facade@saint-gobain.com

16/ SAINT-GOBAIN BUILDING GLASS - FACADE SAINT-GOBAIN BUILDING GLASS - FACADE /17

SPANDRELS



Spandrel glass or "non-vision glass" are used on several buildings to conceal essential components that no one wants to see and are typically located below or on top of the vision glass on each floor of the building.


Spandrel made of glass are often used to have a continuous, smooth fully glazed façade. The spandrel glass can be complementary or contrasting in color when compared to the appearance of the vision glass.

Whatever the aesthetic sought, Saint-Gobain offers complete services to achieve the desired design and propose spandrel glass harmonized to vision glass in order to assure the homogeneity and the full beauty of the façade.

The main component of glass spandrel is the opaque colored glass, comprising uniform enameling on one side of the glass. There are several kinds of spandrel, all presenting some advantages or drawbacks (cost, flexibility, aesthetic, maintenance, thermal performance...).

In the following we are considering 3 configurations:

- a monolitic glass which may comprise a COOL-LITE® ST or ST Bright Silver coating with enamel on #2
- an insulated glazing unit (IGU) with Saint-Gobain solar control coatings on #2 and enamel on #4
- a "Shadow Box" configuration with ventilated cavity, of similar composition comparable to the IGU.



ENAMELING ON COOL-LITE® SOLAR CONTROL COATINGS

Enamels are firstly developed for printing on standard raw soda-lime based float glass. During the tempering process of the glass, the enamels melt and fuse permanently to the glass surface to form a colored ceramic layer. For some applications, there may be a need of enameling coated glass, among others glass spandrels. The processing possibilities are given in the products tables (page 6 to 17). Hereafter a summary for our main COOL-LITE® products families.

COOL-LITE® Family	Enameling and Silk-Printing ⁷
COOL-LITE® ST & STB	Can be enameled ⁸
COOL-LITE® ST BRIGHT SILVER	Can be enameled ⁸ , however , it is not recommended to print COOL-LITE® ST BRIGHT SILVER with dark ceramic paint colors
COOL-LITE® KN II, KNT, SKN II and XTREME II	No common approval for the enameling of silver-based high performance coatings from the COOL-LITE® KN II, KNT, SKN II or XTREME II range

⁷ The processor is responsible for the quality control and quality of the final product. Given the variety of enameling products, different operations and practical experiences, each processor should carry out tests with its own equipment.

Ask us for the processing guidelines for our COOL-LITE® ST, KN (II), SKN (II) or XTREME (II).

Depending of the desired design of the building, the spandrels can have different «look» and «match» with the vision glass in order to achieve an uninterrupted, pure glass facade, simply harmonized with it or inversly fully contrasted for offering to the facade an original rythmed design.

In order to accelerate the decision proces and reduce the number of mock-ups, Saint-Gobain have defined a set of propositions of spandrels harmonizing with the vision glass for the 3 configurations mentioned before.

For each solar control coated glass from the COOL-LITE® SKN (II) and XTREME (II) families, proposition are defined by a coating and the color of the enameled glass (referenced by its RAL) based on a methodology developed by Saint-Gobain⁹.



VISION GLASS (standard double glazing unit with coating on #2)	SPANDREL INSULATED GLAZING UNIT (as illustrated page 18)	SPANDREL VENTILATED SHADOW BOX (as illustrated page 18)	SPANDREL MONOLITHIC GLASS (as illustrated page 18)		
COOL-LITE® XTREME (II) PRODUCTS					
XTREME 70/33 (II)	COOL-LITE® XTREME 70/33 II & PLANICLEAR® RAL 7024 or 7026	_9	COOL-LITE® ST167 with RAL 5008		
XTREME 61/29 (II)	COOL-LITE® XTREME 61/29 II & PLANICLEAR® RAL 7015 or 7026	COOL-LITE® ST167 & PLANICLEAR® RAL 7021	COOL-LITE® ST167 with RAL 7026		
XTREME 50/22 II	COOL-LITE® XTREME 50/22 II & PLANICLEAR® RAL 5008 or 7026	COOL-LITE®ST150 & PLANICLEAR® RAL 7026	_9		
XTREME SILVER II	COOL-LITE® STBS & PLANICLEAR® RAL 5008 or 7026	COOL-LITE® STBS & PLANICLEAR® RAL 5008	COOL-LITE® STBS with RAL 5008		

COOL-LITE® SKN (II) PRODUCTS

SKN 183 (II)	COOL-LITE® SKN 183 II & PLANICLEAR® RAL 7012 or 7015	_9	COOL-LITE® ST150 with RAL 7015
SKN 176 (II)	COOL-LITE® SKN 176 II & PLANICLEAR® RAL 7024 or 7026	_9	COOL-LITE® ST150 with RAL 7015
SKN 165 (II)	COOL-LITE® SKN 165 II & PLANICLEAR® RAL 7024 or 7026	COOL-LITE® ST150 & PLANICLEAR® with RAL 7021	_9
SKN 154 (II)	COOL-LITE® SKN 154 II & PLANICLEAR® RAL 5008 or 7026	COOL-LITE® ST150 & PLANICLEAR® with RAL 5008	COOL-LITE® ST150 with RAL 7012

9 So-called "matching" between spandrel and vision glass is a subjective process and is likely to change depending on the observer as well as external conditions. The suggestions presented here are the best results obtain today based on compatibility and existing product range but are not the only possibilities; for some configuration no satisfying solution can be presented here. It is always recommended to proceed to real observation based on Mock-up.



Accurate predictive physico-realistic rendering helps to refine the choice in specifying and designing with glass for the building facade. It also allows to reduce the influence of the lighting and environmental conditions as well as save time and money. Pictures of the above propositions are now available using Saint-Gobain GlassPro's technology.

With GlassPro Live, Saint-Gobain's on-demand service of glass facade rendering, Architects are allowed to appreciate the look of coated glass as well as spandrels on their own project, as if it was real, before it's even build, with more possibilities in the spandrels configurations.

For more information, contact your local sales and specifier team.

18/ SAINT-GOBAIN BUILDING GLASS - FACADE SAINT-GOBAIN BUILDING GLASS - FACADE

⁸ Contact Saint-Gobain's technical support team for further information and assistance

OUR SERVICES AND TOOLS

GLASSPRO - The Virtual Rendering of Coated Glass

The GlassPro app and GlassPro Live are unique services of Saint-Gobain, bringing new perspectives on building design and glazing prototyping through digital simulation. Accurate predictive glass façade 3D physico-realistic rendering reduces the need for physical glass mock-ups, which opens the door to a more sustainable approach for prototyping, and accelerates the decision-making process with regards to selecting the ideal glazing with the desired aesthetics corresponding to your design intention.



GLASSPRO App - The iPad application

GLASSPRO app is an application for Apple iPad which enables the user to visualize virtually all Saint-Gobain's standard glazing products on a standard building façade.

Choose and compare two types of glazing with a personalized rendering of a glazing product under a variety of lightning conditions and several interior design settings through two different environments (urban and countryside to avoid representative issues).

This app, downloadable on the Apple store shows an accurate and realistic virtual rendering, based on physical properties of the glass.



GLASSPRO Live - The on-demand service

GLASSPRO Live is Saint-Gobain's on-demand service of glass facade rendering. It allows architects to appreciate the look of Saint-Gobain Glazing products on their own building, as if it was real, before it's even built!

Ask for your glazing configuration to be represented under a variety of lightning conditions and several interior design settings thanks to our 2 scenes just like in the app. With our on-demand service, you can also ask for us to stimulates a realistic image of different glazing products on your own building facade.

Visualize and compare all Saint-Gobain glazing products on high definition 3D synthesis images called "physico-realistic" under a variety of lightning conditions and even on your own building 3D rendering.

To request the service, please contact your local sales and specifier team.

Website SAINT-GOBAIN GLASS



Discover our product range to find the ideal glass for your project which responds the best to your expectations.

Find also our services, the apps and calculation tools you need in the website www.saint-gobain-glass.com

You may select your area/country to have our local offer and dedicated products

INSTAGLASS - The Reference Project Website for Glass Facades



Come and explore our architectural references showing a wide range of glass solutions, innovations and aesthetic options for the building envelope.

Discover inspirational sustainable design of living spaces and distinctive building that make our environment worth living in

www.saint-gobain-glass.com/instaglass

CALUMEN: The Reference of Calculation



Determine the light, energy, thermal or acoustic performances of your glazing; or to find a suitable glazing for your project based on its performance values.

Personalize settings such as type of glazing, type of coating, glass and cavity thickness.

Specify a project, make comparisons between our products, change the configurations and obtain the right product.

CalumenLive is available on www.calumenlive.com

CALUWIN: Comfort by numbers



Calculate quickly and easily:

- The whole U-value (Uw value)
- Surface temperatures
- The condensation risk in the glass edge area
- Energy savings thanks to warm edge spacer

Caluwin is available on www.caluwin.com

GLASS VISION: The realistic online tool for deco and design glass



GLASS VISION supports you online in finding your first ideas - quickly, easily, free of charge and without registration.

The inspiration tool includes many classic interior scenarios for both private homes and commercial properties, as well as numerous materials, colours and styles of furnishing.

Choose between kitchen, living room, bathroom, office, retail, hotel lobby and hotel rooms, and with just a few clicks test which colours, glasses and textures go best together there.

www.saint-gobain-glass.com/visualizer

GREEN BUILDING WEBSITE: For sustainable habitat



Discover how all Saint-Gobain products and solutions can contribute to achieving credits in green building certifications.

Explore our certifications among different international labels such as LEED, BREEAM, DGNB, HQE or even WELL.

Find all the needed documentation for certification process. Saint-Gobain solutions covers numerous applications such as facades, ceilings, floors, foundations, roofs, walls, and many others.

www.greenbuilding.saint-gobain.com

20/ SAINT-GOBAIN BUILDING GLASS - FACADE SAINT-GOBAIN BUILDING GLASS - FACADE

MAKING THE WORLD A BETTER HOME

Together with and for our customers, we design, manufacture and distribute materials and solutions that have a positive impact on everyone's life and provide well-being, quality of life and performance, while caring for the planet.



This commitment is driving our Glass Forever program, with the help of all our stakeholders, employees, customers, partners, and suppliers.

From small seeds to big rivers, our vision is to grow our business and to differentiate, while improving our environment footprint and increasing our contribution to people's wellbeing.

BUILDING GLASS

Saint-Gobain Tower
12 place de l'Iris
92400 Courbevoie
FRANCE

www.saint-gobain-glass.com

glass.facade@saint-gobain.com



Saint-Gobain Building Glass issued 18 verified Environmental Product Declarations (EPD) covering actually more than 165 different products.

They describe in detail the glazing's environmental footpint, from raw material extraction to exiting the plant. Today, this is one of the key requirements for green building certificates like LEED, BREEAM, DGNB and HQE.

in

Saint-Gobain Glass Facade

